

HUDCO Industrial Products, Inc.

Anti-Abrasive

Ballistic Grade Aramid Fiber Reinforced Carbide Repair Compound**HUDCO Formula 2000**

The dense concentration of silicon carbide granules in HUDCO Formula 2000 high strength epoxy resins resists the abrasive and corrosive wear found in chutes, pumps, fan housings and other similar equipment.

HUDCO Formula 2000 adheres to all metals, concrete, wood and some plastics and cures at room temperature without shrinkage. It also conforms to odd shapes and can be easily applied without special skills.

Reinforced with Ballistic Grade Aramid Fiber

After 12 years of unequalled performance, HUDCO in 1994 reformulated Formula 2000 to include ballistic grade aramid fiber reinforcement in the polymer matrix. The addition of ballistic grade aramid fiber, one of the toughest materials in existence, has significantly improved the phenomenal properties of HUDCO Formula 2000. The unique concept of using ballistic grade aramid fiber to reinforce the matrix of HUDCO Formula 2000 demonstrates HUDCO's commitment to world class technology.

Beneficial Properties of HUDCO Formula 2000

- Non-machinable.
- Requires no special application skills.
- Does not shrink or expand.
- Conforms quickly to odd shapes.
- Adheres to all metals, concrete, wood and some plastics.

Typical Applications

HUDCO Formula 2000 provides excellent wear protection in a wide range of applications including slurry pump housings, screw conveyors, pneumatic conveying equipment, and other areas subject to abrasive wear.

Physical Properties

Compressive Strength – ASTM D-695	18,000 PSI
Shear Strength	8,500 PSI
Pot Life	45 Min. @ 70° F
Temperature max	275° F

Packaging

Resin	Curing Agent	Kit Weight
4 lbs.	1lb.	5 lbs.
16 lbs.	4 lbs.	20 lbs.



This reference guide is not intended as a substitute for the product label for the products referenced herein. Product labels for the above products contain important precautions, directions for use and product warranty and liability limitations that must be read before using the product. Applicators must be in possession of the product label(s) at the time of application. Always read and follow all label directions and precautions.

Application Instructions

Surface Preparation:

(A) Surfaces must be clean and sound. Remove grease, oil, or other foreign material with acetone or detergent wash. Roughen the surface by sandblasting or sanding with course abrasive using a cross-hatch pattern. Etching the surface with an appropriate acid is acceptable if followed by thorough flushing and neutralizing with clean water.

(B) Surface temperature must be completely dry with a minimum surface temperature of 75° F before applying Hudco Formula 2000.

Mixing: Mix 4 parts of HUDCO Formula 2000 Resin to 1 part of HUDCO Formula 2000 Hardener by weight or volume. Kits are supplied in the correct ratio. Ensure that the sides of the mixing container are scraped into the mixture. Mix several minutes, until no streaks are observed and consistent color is achieved.

Application: Apply product to prepared surface and use supplied tools to achieve desired finish.

Curing: At 75° F, product will gel in 20 min. Initial cure will occur in 2 - 4 hours. Final cure occurs in 24 hours.

Safety Precautions

CAUTION: For Industrial Use Only. Keep Away From Children.

HUDCO Formula 2000 Resin contains epoxy resin which is harmful if swallowed. After prolonged exposure it may irritate skin and cause sensitization and/or dermatitis.

HUDCO Formula 2000 Curing Agent contains organic amine compounds which are harmful if swallowed. After prolonged exposure or repeated skin contact it may cause irritation, sensitization and/or dermatitis.

Emergency and First Aid Procedures

- Eye Contact - Irrigate with clean water for 15 minutes and call a physician.
- Skin Contact - Wash with soap and water.
- Inhalation - Remove to fresh air and provide oxygen if necessary.
- Ingestion - Call a physician at once. Give milk or white of egg beaten with water. Then give a teaspoon of salt in a glass of warm water to induce vomiting.

Protection Procedures

If used in a confined or an enclosed area, use an air supplied mask or respirator with canister for organic vapors and provide mechanical exhaust ventilation. Use protective gloves, safety glasses, and protective clothing. Avoid contact with skin and clothing. Contaminated clothing should be laundered before wearing again. Contaminated shoes should be thoroughly cleaned before wearing again.

Storage

HUDCO Formula 2000 Resin and Curing Agent should be stored in a cool, dry area. Shelf life is a minimum of one year in unopened containers when stored at 70° F – 85° F.

Warranty

Because the storage, handling and application of these materials are beyond our control, we can accept no liability for the results of their use. Our liability is limited only to replacement of any material proven defective in manufacture. We suggest users try small applications to determine the suitability of the product for their intended use.

HUDCO Industrial Products, Inc.

3100 Morgan Road
Bessemer, AL 35022
1-800-247-9908

Fax: 205-425-4011
Email: sales@hudcoinc.com
Website: www.hudcoinc.com



This reference guide is not intended as a substitute for the product label for the products referenced herein. Product labels for the above products contain important precautions, directions for use and product warranty and liability limitations that must be read before using the product. Applicators must be in possession of the product label(s) at the time of application. Always read and follow all label directions and precautions.